



## Technical Data Sheet

**S 06**  
**Version Nr. 6**

		Glass Fibre Netting	
	Characteristic	SSA – 0808 – SM	Test method
1.	Size of hole, mm	~ 8 mm	Comp. Method PP - Q - S 05
2.	Weave	Leno	
3.	Construction of fabric, tex	warp: EC 11 – 204 Z 20 weft: EC 11 – 408	DIN 12654
4.	Thread count per 10 cm	warp: (12x2) +/- (1x2) weft: 12 +/- 1	DIN 53853
5.	Width, cm	100 + 1/- 0	DIN EN 1773
6.	Weight, g/m <sup>2</sup>	> 115	DIN EN 12127
7.	L.O.I., %	18 - 25	DIN ISO 1887
8.	Tensile strength, N/50 mm	warp: > 1500 weft: > 1500	EN ISO 13934.1
8.1	Tensile strength, N/50 mm After ageing ( ETAG 004)	warp: > 900 weft: > 800	
9.	Roll length, nom., m	50	

### Packing, Storage, Transporting

#### Packing:

- netting wound on the core with inside diameter 50 or 76 mm,
- each roll wrapped in the plastic,
- rolls are fastened on the wooden pallet or put in the carton 20 or 24 rolls/ pallet.

#### Transporting, Storage:

- goods have to be stored and transported in the producer's packing,
- clean and dry storage.