

Technical Data Sheet

S 29
Version Nr. 6

		Glass Fibre Netting	
	Characteristic	SSA-1010-SM	Test method
1.	Size of hole, nom., mm	~ 10 × 10	ETAG 004
2.	Weave	Leno	
3.	Construction of fabric, tex	warp: EC13-272z20 weft: EC16-600	DIN 12654
4.	Thread count per 10 cm	warp: (10x2) +/- (1x2) weft: 11 +/- 1	DIN 53853
5.	Width, cm	100 + 1/- 0	DIN EN 1773
6.	Weight, g/m ²	≥ 145	ETAG 004
7.	Ash content, %	75 - 82	ETAG 004
8.	Tensile strength, N/50 mm	warp: ≥ 1700 weft: ≥ 1700	ETAG 004
8.1	Tensile strength, N/50 mm after ageing (ETAG 004)	warp: ≥ 850 weft: ≥ 850	
9.	Roll length, nom., m	100	

Packing, Storage, Transporting

Packing:

- netting wound on the core with inside diameter 45 or 50 mm;
- each roll wrapped in the plastic foil;
- rolls are placed into a cardboard box;
- the box is fastened on a wooden pallet.

Transporting, Storage:

- goods have to be stored and transported in the producer's packing,
- clean and dry storage.